




RM type power ferrite product series

  															
Fig.1		Fig.2		Fig.3											
Specification	Fig.	Dimensions (mm)								Effective parameter			Inductance AL(nH/N2)		Weight (g/set)
		A1	A2	B	C	D	E	F	G	Ae(mm²)	Le(mm)	Ve(mm³)	FX44	FX95	
RM6-2	1	17.80±0.30	14.60±0.35	6.30±0.15	8.1±0.15	6.30±0.15	12.70min	4.30±0.20	9.0 min	34,00	31,56	1073,04	2100±25%	2600±25%	5,40
RM7	1	19.90±0.40	16.85±0.35	6.70±0.15	7.05±0.15	7.05±0.15	15.10±0.30	4.45±0.15	11.2 min	36,74	34,88	1285,60	1900±25%	2800±25%	7,20
RM8-2	2	22.75±0.50	19.50±0.40	8.70±0.20	10.80±0.30	8.4±0.20	17.30min	5.90±0.20	11.00 min	59,90	42,30	2533,77	3200±25%	4000±25%	12,85
RM10-4	2	27.85±0.65	24.15±0.55	9.35±0.15	13.25±0.25	10.7±0.20	21.65±0.45	6.35±0.15	13.5 min	89,90	47,95	4310,00	4500±25%	5200±25%	21,90
RM10-1	3	28.00±0.50	25.30±0.50	9.30±0.20	13.25±0.20	10.7±0.20	22.50±0.50	6.60±0.20	14.5 min	85,60	49,20	4210,40	4500±25%	5000±25%	21,60
RM12	2	36.90±0.70	29.20±0.60	12.25±0.20	15.90 ^{+0.2} _{-0.3}	12.6±0.20	25.50 ^{+0.5} _{-0.6}	8.55±0.20	13.4 min	140,00	56,90	7970,0	5200±25%	6200±25%	45,80
RM14	2	41.60±0.60	34.20±0.50	14.40±0.10	18.70±0.30	14.75±0.25	29.50±0.50	10.60±0.15	17.0 min	180,00	73,80	13283,0	6000±25%	7500±25%	66,50
RM14	2	41.60±0.60	34.20±0.50	14.40±0.10	18.70±0.30	14.75±0.25	29.50±0.50	10.60±0.15	17.0 min	180,00	73,80	13283,0	6000±25%	7500±25%	66,50

Remark: Testing conditon for AL 1KHz, 0.3V, 100Ts

The above is the usually type, we can redesign according to costomer's request